

<p>Surface Preparation</p>	<p>All surface to be coated must be clean, dry and free from contamination in accordance to ISO 8504. Oil and grease must be removed by solvent cleaning in accordance to SSPC - SP1.</p> <p>Abrasive blast clean to Sa 2.5 (ISO 8501 - 1:2007) or SSPC - SP6. If oxidation has occurred between the blasting time and application of Korepox 515P, the surface should be reblasted to the specified visual standard.</p> <p>A surface profile of 40 to 75 microns is recommended.</p>
<p>Application Temperatures</p>	<p>Air and surface temperature should be between 20 to 45 deg. C and surface temperature must be minimum 3 deg. C above dew point.</p>
<p>Mixing</p>	<p>Korepox 515P is supplied in 2 components, Part A - Base and Part B - Hardener. The Hardener (Part B) should be slowly added to the Base (Part A) while continuous stirring with a mechanical agitator. Mixed materials should be filtered using a 60 mesh screen prior to application and should be constantly agitated in the pot during application.</p>
<p>Repair / Top Coating</p>	<p>Damaged areas should be spot blast to Sa 2.5 and touch up with a coat of Korepox 515P. Whenever spot blasting is deemed not possible, Galvany 800, one pack zinc primer or K' Mastic 5000 is recommended to be used for repair of damaged areas.</p>
<p>Product Limitations</p>	<p>Care should be taken to avoid the application of Korepox 515P to dry film thickness in excess of 150 microns. Over application of Korepox 515P will affect both the minimum overcoating intervals and handling times.</p> <p>Care must be taken to avoid dry spray during applications and excessive dry spray may lead to pinholing of subsequent coats.</p> <p>When Korepox 515P is left to weather before application of subsequent coats, all visible zinc salts are to be removed prior to application of subsequent coats.</p>
<p>Safety Precaution</p>	<p>This product is flammable and must be kept away from any source of ignition. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately. Keep out of reach of children.</p>

Disclaimer: The above information is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given information without prior notice.