

<p>Surface Preparation</p>	<p>All surface to be coated must be clean, dry and free from contamination in accordance to ISO 8504. Oil and grease must be removed by solvent cleaning in accordance to SSPC - SP1.</p> <p>Abrasive blast clean to Sa 2.5 (ISO 8501-1:2007) or SSPC - SP6. If oxidation has occurred between the blasting time and application of Korepox 514P, the surface should be reblasted to the specified visual standard.</p> <p>An average surface profile up to 50 microns is recommended.</p>
<p>Application Temperatures</p>	<p>Air and surface temperature should be between 20 to 45 deg. C and surface temperature must be minimum 3 deg. C above dew point.</p>
<p>Mixing</p>	<p>Korepox 514P is supplied in 2 components, Part A - Base and Part B - Hardener. The Hardener (Part B) should be slowly added to the Base (Part A) while continuous stirring with a mechanical agitator.</p>
<p>Repair / Topcoating</p>	<p>Damaged areas should be spot blast to Sa 2.5 and touch up with a coat of Korepox 514P. Whenever spot blasting is deemed not possible, K' Mastic 5000 is recommended to be used for repair of damaged areas.</p>
<p>Product Limitations</p>	<p>In common with all epoxies, Korepox 514P will chalk and discolour on external exposure and weathering and this phenomenon is not detrimental to the anti-corrosive performance.</p> <p>Application of thickness more than 50 microns in a single coat will extend both the minimum coating intervals and handling times.</p> <p>For brush and roller applications, multiple coats may be required to achieve the required DFT.</p>
<p>Safety Precaution</p>	<p>This product is flammable and must be kept away from any source of ignition. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately. Keep out of reach of children.</p>

Disclaimer: The above information is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given information without prior notice.