





<b>Surface Preparation</b>	All surface to be coated must be clean, dry and free from contamination in accordance to ISO 8504. Oil and grease must be removed by solvent cleaning in accordance to SSPC - SP1.
<b>Application Temperatures</b>	Air and surface temperature should be between 20 to 45 deg. C and surface temperature must be minimum 3 deg. C above dew point.
<b>Mixing</b>	Stir content thoroughly with a mechanical stirrer until uniformly mixed.
<b>Repair / Topcoating</b>	Damaged areas should be touch up with a coat of PolyEtch 100.
<b>Product Limitations</b>	<p>In common with all epoxies, PolyEtch 100 will chalk and discolour on external exposure and weathering and this phenomenon will affect the adhesion performance of applications for subsequent coating.</p> <p>Application of thickness more than 20 microns may lead to loss of adhesion properties.</p> <p>The product is not designed for opacity properties.</p>
<b>Safety Precaution</b>	This product is flammable and must be kept away from any source of ignition. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately. Keep out of reach of children.

Disclaimer: The above information is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given information without prior notice.