

# Technical Data Sheet



## KCC AURORA Prestige

### Special Effects Paint

#### Product Description

KCC AURORA Prestige is a premium semi-transparent acrylic water based special effects paint. It is used as a metallic or pearlescent effect glaze coat over coloured wall to create aesthetically unique feature walls. It is DIY friendly, low VOC, low odour, and eco-friendly which is free from lead, mercury, APEO and formaldehyde.

#### Recommended Use

Interior use for concrete, masonry surfaces, walls, ceilings and soft board surfaces suitable for new and repainting projects.

#### Product Information

Binder	: Full Acrylic
No. of Components	: 1
Solids (% by Volume)	: 26 ± 2 %
Flash Point	: Non Flammable
Colour	: Pearl, Gold, Antique Gold (Please consult KCC representative for custom colours)
Finish	: Sheen, Metallic

#### Application Information

Substrate	: Concrete, Masonry, Plaster
Recommended No. of Coats	: 1
Recommended Wet Film Thickness	: 50 μm / Coat
Recommended Dry Film Thickness	: 30 μm / Coat
Theoretical Spreading Rate @ 30μm	: 9 m <sup>2</sup> / L / Coat
<small>(Does not include substrate condition and loss factors)</small>	
Drying Agent	: Evaporation, Coalescence
Drying Time	: Touch Dry 30 min Hard Dry 2 to 3 hr

#### Application Methods

Applied By	: Sponge, Brush
Thinner	: Clean Water
Clean Up	: Clean Water

#### Packaging & Storage

Packaging	: 1L
Shelf Life	: 12 months - Unopened
Storage	: Cool, dry and well ventilated area away from heat and direct sun light. Lid must be kept tightly closed.

Disclaimer : The above information is given to the best of our knowledge based on laboratory testing and practical experiences. The information in this data sheet may be subject to changes from time to time and without notice due to production refinements arising from continuing research and evaluation programmes, which may occasionally result in marginal changes in the coating properties.

## Surface Preparation

### **New Masonry Substrate**

Allow all new surfaces to dry out thoroughly, preferably for at least 28 days drying time or check moisture content for less than 16%. Surface imperfections, misalignments and protrusions shall be made good and patched up. All surface contaminants such as laitance, dust and loose cement shall be removed using scraper, sandpapers and clean stilt brushes.

### **Previously Painted Surfaces**

All loose or defective paintwork or powdery residues shall be thoroughly removed. Treat any areas affected by mould, lichens, algae and moss with "KCC Fungicidal Solution". Make good minor defects with an appropriate suitable putty sealant. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

## Typical Recommended Painting System

### **Substrate: Concrete, Masonry, Plaster**

<u>System</u>	<u>Product</u>	<u>No. of Coats</u>
Sealer	AURORA Primer	1
Finish	KCC AURORA Sheen	2
Glaze Coat	KCC AURORA Prestige	1

### **Substrate: Previously Painted Concrete, Masonry, Plaster**

<u>System</u>	<u>Product</u>	<u>No. of Coats</u>
Sealer	AURORA Primer (Optional)	1
Finish	KCC AURORA Sheen	2
Glaze Coat	KCC AURORA Prestige	1

## Application & Cleaning Instructions

Paint is ready for use after thorough stirring. Thinning is not normally necessary, however, if required for better workability, do not exceed 5% of dilution ratio. Clean up equipment with water immediately after use.

## Health & Safety

Ensure good ventilation during application and drying. Avoid contact with skin and eyes. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. After contact with skin, wash immediately with plenty of soap and water. During spray application, do not breathe in mist and wear suitable respiratory protective equipment. Keep out of reach of children.

Disclaimer : The above information is given to the best of our knowledge based on laboratory testing and practical experiences. The information in this data sheet may be subject to changes from time to time and without notice due to production refinements arising from continuing research and evaluation programmes, which may occasionally result in marginal changes in the coating properties.